

SKIM COAT

Product Data Sheet



PRODUCT NAME	CODE	COLOUR
KG Skim Base	B10 / WB10	Grey / White
PRODUCT DESCRIPTION		
Premium quality polymer modified cementitious skim base coat provides superior bonding to internal shear/ concrete walls or ceilings and plastered wall surfaces.		

TECHNICAL DATA

DRY BULK DENSITY	COATING THICKNESS	WATER FOR MIXING
1.2 t/m ³	2 - 3 mm	30% ± 2% (7.5 Litre/25kg bag) (12 Litre/40kg bag)
BINDER	COVERAGE	TENSILE ADHESION
Ordinary Portland Cement	1.2 kg/m ² per mm thick	≥ 0.6 N/mm ²
COMPRESSIVE STRENGTH	FLEXURAL STRENGTH	POT LIFE
≥ 4 N/mm ²	≥ 2 N/mm ²	1 Hour
PACKAGING	STORAGE	
25kg / 40kg	6 Months	

INSTRUCTION FOR USE

SURFACE FOR USE

Surfaces to be skimmed must be sound, clean and free from any contamination. Wet the surface prior to application in hot and dry conditions.

MIXING

Mix the product thoroughly with approximately 30% by weight of clean water using an electric mixer with attached stirrer for 3 - 5 minutes, until a homogeneous mix that is free from lumps is achieved.

APPLICATION

Apply on the surface manually using a steel trowel or spatula, or using a spray plastering machine.

FINISHES

Apply KG-Mix Skim Finish (F10/WF10) for a smooth finish.

FIRE RESISTANCE

This product is non-combustible.

SAFETY PRECAUTION

This product contains cement additives and may cause irritation when in contact with skin or eyes. In case of any contact, wash thoroughly with clean water. If irritation persists, seek immediate medical attention.

DISCLAIMER:

All information contained herein is only intended to give a fair description of the products and their capabilities under such specific test conditions.
However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.



KG-MIX (M) SDN BHD (705033-K)

PT 14498, Persiaran BG Perdana 6, Taman Batu Gajah Perdana, 31550 Pusing, Perak.

Tel: +6(05) 3668323 | Fax: +6(05) 3668363 | Email: inquiry@kgmix.com