



PRODUCT NAME	CODE	COLOUR
KG Skim Base External	B10E / WB10E	Grey / White

PRODUCT DESCRIPTION
Premium quality polymer modified water resistant cementitious skim base coat provides superior bonding to internal and external shear/ concrete walls or ceilings, block wall and plastered wall surfaces.

TECHNICAL DATA

DRY BULK DENSITY	COATING THICKNESS	WATER FOR MIXING
1.2 t/m ³	3 - 5 mm	30% ± 2% (12 Litre/bag)
BINDER	COVERAGE	TENSILE ADHESION
Ordinary Portland Cement	1.2 kg/m ² per mm thick	≥ 0.8 N/mm ²
COMPRESSIVE STRENGTH	FLEXURAL STRENGTH	POT LIFE
≥ 8 N/mm ²	≥ 2 N/mm ²	1 Hour
PACKAGING	STORAGE	
40kg	6 Months	

INSTRUCTION FOR USE

SURFACE FOR USE

Surfaces to be skimmed must be sound, clean and free from any contamination. Wet the surface prior to application in hot and dry conditions.

MIXING

Mix the product thoroughly with approximately 30% by weight of clean water using an electric mixer with attached stirrer for 3 - 5 minutes, until a homogeneous mix that is free from lumps is achieved.

APPLICATION

Apply on the surface manually using steel trowel/ spatula or using spray plastering machine.

FINISHES

Apply KG-Mix Skim Finish External (F10E), for a smooth finish.

FIRE RESISTANCE	SAFETY PRECAUTION
This product is non-combustible.	This product contains cement additives and may cause irritation when in contact with skin or eyes. In case of any contact, wash thoroughly with clean water. If irritation persists, seek immediate medical attention.

DISCLAIMER:

All information contained herein is only intended to give a fair description of the products and their capabilities under such specific test conditions.

However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.



KG-MIX (M) SDN BHD (705033-K)

PT 14498, Persiaran BG Perdana 6, Taman Batu Gajah Perdana, 31550 Pusing, Perak.

Tel: +6(05) 3668323 | Fax: +6(05) 3668363 | Email: inquiry@kgmix.com