



PRODUCT NAME	CODE	COLOUR
KG Joint Compound	F2	White

PRODUCT DESCRIPTION
KG Joint Compound is ready-to-use for smoothing uneven plastering walls, painted surfaces, plaster ceiling joints and gypsum board joints to give a smooth and seamless finishing before applying a coating. It can also used for taping, finishing gypsum board joints, filing, covering and final touch-up coats in interior gypsum board applications. It can also be used to repair cracks for skim-coat and brick wall surfaces.

TECHNICAL DATA

BINDER	COATING	DRYING TIME
Vinyl Polymer	For Skim 2 to 3 Coats For Joint 3 Coats	For Skim 2 to 3 hours For Joint 4 to 5 hours
COVERAGE	PACKAGING	STORAGE
1.8m ² to 2.0m ² per kg per coat	25KG/Drum	12 Months in original packing

INSTRUCTION FOR USE

SURFACE FOR PREPARATION

The surfaces to be applied must be clean, firmly fixed and free from any contamination on the substrate.

APPLICATION

For Flushing Joints:

1. Evenly fill board gap with joint compound.
2. Fixed perforated paper tape / fibre tape and press down into freshly applied joint compound.
3. Applied second or final coat of joint compound when first coat is sufficiently set.
4. Allow joint compound to sufficiently set, sanding lightly with fine sand paper to obtain a very smooth finish.

For Repairing of Plaster Shrinkage Crack:

1. Score the hairline crack to open it edges to increase the surfaces for the compound to bond properly, brush off any loose particles.
2. Apply a layer of compound firmly over the crack, allow to set.
3. Apply second layer to evenly cover the crack and allow to set. Apply third layer if necessary for a white smooth finish.

FIRE RESISTANCE	SAFETY PRECAUTION
This product is non-combustible.	This product contains cement additives and may cause irritation when in contact with skin or eyes. In case of any contact, wash thoroughly with clean water. If irritation persists, seek immediate medical attention.

DISCLAIMER:

All information contained herein is only intended to give a fair description of the products and their capabilities under such specific test conditions.

However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.



KG-MIX (M) SDN BHD (705033-K)

PT 14498, Persiaran BG Perdana 6, Taman Batu Gajah Perdana, 31550 Pusing, Perak.

Tel: +6(05) 3668323 | Fax: +6(05) 3668363 | Email: inquiry@kgmix.com