

SKIM COAT

Product Data Sheet



PRODUCT NAME	CODE	COLOUR
KG Wall Plaster	F38	Grey

PRODUCT DESCRIPTION

High quality polymer modified cementitious wall finish top coat provides superior bonding onto internal base coat, render coat and plastered wall to give a fine and smooth finishing before painting work.

TECHNICAL DATA

DRY BULK DENSITY	COATING THICKNESS	WATER FOR MIXING
1.1 t/m ³	1 - 3 mm	36% ± 2% (9 Litre/bag)
BINDER	COVERAGE	TENSILE ADHESION
Ordinary Portland Cement	1.0 kg/m ² per mm thick	≥ 0.5 N/mm ²
COMPRESSIVE STRENGTH	FLEXURAL STRENGTH	POT LIFE
≥ 4 N/mm ²	≥ 4 N/mm ²	1 Hour
PACKAGING	STORAGE	
25kg	6 Months	

INSTRUCTION FOR USE

SURFACE FOR USE

Surfaces to be plastered must be sound, clean and free from any contamination. Wet the surface prior to application in hot and dry conditions.

MIXING

Mix the product thoroughly with approximately 36% by weight of clean water using an electric mixer with attached stirrer for 3 - 5 minutes, until a homogeneous mix that is free from lumps is achieved.

APPLICATION

Apply to the surface manually using a steel trowel/spatula or with a spray plastering machine.

FIRE RESISTANCE	SAFETY PRECAUTION
-----------------	-------------------

This product is non-combustible.

This product contains cement additives and may cause irritation when in contact with skin or eyes. In case of any contact, wash thoroughly with clean water. If irritation persists, seek immediate medical attention.

DISCLAIMER:

All information contained herein is only intended to give a fair description of the products and their capabilities under such specific test conditions.

However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.



KG-MIX (M) SDN BHD (705033-K)

PT 14498, Persiaran BG Perdana 6, Taman Batu Gajah Perdana, 31550 Pusing, Perak.

Tel: +6(05) 3668323 | Fax: +6(05) 3668363 | Email: inquiry@kgmix.com