

# SKIM COAT

Product Data Sheet



PRODUCT NAME	CODE	COLOUR
KG Wall Finish	F88 / WF88	Grey / White

**PRODUCT DESCRIPTION**

Eco-friendly and high quality polymer modified cementitious wall finish top coat that provides superior bonding onto internal base coat, render coat and plastered wall to give a fine and smooth finishing before painting work.

## TECHNICAL DATA

<b>DRY BULK DENSITY</b>	<b>COATING THICKNESS</b>	<b>WATER FOR MIXING</b>
1.1 t/m <sup>3</sup>	1 - 3 mm	38% ± 2% (15.2 Litre/bag)
<b>BINDER</b>	<b>COVERAGE</b>	<b>TENSILE ADHESION</b>
Ordinary Portland Cement	1.0 kg/m <sup>2</sup> per mm thick	≥ 0.4 N/mm <sup>2</sup>
<b>COMPRESSIVE STRENGTH</b>	<b>FLEXURAL STRENGTH</b>	<b>POT LIFE</b>
≥ 4 N/mm <sup>2</sup>	≥ 1.2 N/mm <sup>2</sup>	1 Hour
<b>PACKAGING</b>	<b>STORAGE</b>	
40kg	6 Months	

## INSTRUCTION FOR USE

### SURFACE FOR USE

Surfaces to be skimmed must be sound, clean and free from any contamination. Wet the surface prior to application in hot and dry conditions.

### MIXING

Mix the product thoroughly with approximately 38% by weight of clean water using an electric mixer with attached stirrer for 3 - 5 minutes, until a homogeneous mix that is free from lumps is achieved.

### APPLICATION

Apply to the surface manually using a steel trowel/ spatula or with a spray plastering machine.

FIRE RESISTANCE	SAFETY PRECAUTION
This product is non-combustible.	This product contains cement additives and may cause irritation when in contact with skin or eyes. In case of any contact, wash thoroughly with clean water. If irritation persists, seek immediate medical attention.

### DISCLAIMER:

All information contained herein is only intended to give a fair description of the products and their capabilities under such specific test conditions. However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.



**KG-MIX (M) SDN BHD (705033-K)**  
 PT 14498, Persiaran BG Perdana 6, Taman Batu Gajah Perdana, 31550 Pusing, Perak.  
 Tel: +6(05) 3668323 | Fax: +6(05) 3668363 | Email: inquiry@kgmix.com