



PRODUCT NAME	CODE	COLOUR
KG Render Premium	P22	Grey

PRODUCT DESCRIPTION
Premium quality polymer modified pre-mixed thin to medium bed plaster / render specially formulated as an alternative to conventional site mix mortar which provides superior bonding with direct application onto shear/ concrete substrates. Suitable for use on all internal and external wall.

## TECHNICAL DATA

DRY BULK DENSITY	RENDERING THICKNESS	WATER FOR MIXING
1.65 t/m <sup>3</sup>	5 - 15 mm	20% ± 2% (8 Litre/bag)
BINDER	COVERAGE	TENSILE ADHESION
Ordinary Portland Cement	1.5 kg/m <sup>2</sup> per mm thick	≥ 0.8 N/mm <sup>2</sup>
COMPRESSIVE STRENGTH	FLEXURAL STRENGTH	POT LIFE
≥ 8 N/mm <sup>2</sup>	≥ 1.0 N/mm <sup>2</sup>	1 Hour
PACKAGING	STORAGE	
40kg	6 Months	

## INSTRUCTION FOR USE

### SURFACE FOR USE

Surfaces to be plastered must be sound, clean and free from any contamination. Wet the surface prior to application in hot and dry conditions.

### MIXING

Mix the product thoroughly with approximately 20% by weight of clean water using an electric mixer with attached stirrer for 3 - 5 minutes until a homogeneous mix that is free from lumps.

### APPLICATION

Apply to the surface manually using a steel trowel/ spatula or with a spray plastering machine. For thicknesses above 15mm, we recommend applying a scratch coat of 6 to 8mm. The subsequent coat should be applied once the scratch coat has sufficiently dried.

### FINISHES

For a matt coarse finish, lightly pass over the surface with a damp float. For a smooth finish, apply KG-Mix Skim Finish Product (F10/WF10/F10E).

FIRE RESISTANCE	SAFETY PRECAUTION
-----------------	-------------------

This product is non-combustible.	This product contains cement additives and may cause irritation when in contact with skin or eyes. In case of any contact, wash thoroughly with clean water. If irritation persists, seek immediate medical attention.
----------------------------------	--

### DISCLAIMER:

All information contained herein is only intended to give a fair description of the products and their capabilities under such specific test conditions. However, it does not constitute an offer of warranty by the manufacturer nor a guarantee of its accuracy or completeness in describing the performance or suitability of the various products.



**KG-MIX (M) SDN BHD (705033-K)**  
 PT 14498, Persiaran BG Perdana 6, Taman Batu Gajah Perdana, 31550 Pusing, Perak.  
 Tel: +6(05) 3668323 | Fax: +6(05) 3668363 | Email: inquiry@kgmix.com